

Blue Printed backing

End Use Classification (BS 5808: 1991): L/U, Luxury Use

Excellent thermal insulation

High degree of impact sound insulation

Guaranteed for the serviceable lifetime of the carpet when used in the recommended locations

Roll size: 1.37 m x 11.0 m

Suitable for stretch-fit installation of carpets

Specification	BS Requirements	Result	Method
Nominal square weight		770 g/m ²	
Nominal density		110 kg/m ³	
Nominal roll weight		28 lbs	
Nominal thickness		7.00 mm	BS 4051
Mean original thickness from nominal thickness	Maximum 12%	2.5 %	
Difference between max. & min. original thicknesses	Maximum 3mm	0.22mm	
Work of compression	Minimum 50 J/m ² after dynamic loading for 1000 impacts	119 J/m ²	BS 4098 & BS 4052
Compression after dynamic loading	Minimum 2mm, maximum 7mm after 1000 impacts	4.4 %	
Retention of work of compression	Minimum 40% of original after 1000 impacts	89.3%	
Breaking strength - length	Minimum 40N	163.9N	BS 2576
Breaking strength - width		127.1N	
Extension under force - length	Maximum 10% @ 40N	8.6%	
Extension under force - width		2.39%	
Loss in thickness after dynamic loading	Maximum 15% after 1000 impacts	4.4mm	BS 4052
Loss in thickness after static loading	Maximum 15% after 24hrs loading & recovery	5.4 %	BS 4939
Resistance to cracking	Not greater than 50mm	Pass	BS 5808
Odour		No objectionable odour	
Flammability	Notes	Result	Method
Hot metal nut test	Tested in Interfloor laboratory	Low radius of effects of ignition	BS 4790 & BS 5287
Thermal Properties			
Thermal resistance		2.05 togs	BS 4745
Acoustic Properties			
Weighted reduction in impact sound pressure level (Delta Lw)		Under test	BSEN ISO 140-8: 1998 and BSEN ISO 717-2: 1997

Item Code TACOSYWALK

Issue No. 1

Issue Date 16-Nov-06

Page No. 1 of 1

Please note: This document does not constitute a manufacturing specification. It details important technical performance and physical characteristics of the product only. Please contact the Technical Department for any further information.

Interfloor Ltd, Broadway, Haslingden, Rossendale, Lancashire. BB4 4LS.

Tel: +44(0)1706 213131 Fax: +44(0)1706 260800 Email: technical@interfloor.com Web: www.interfloor.com